## AMENDMENT

## (UNDER ARTICLE 11 OF THE LAW)

To: Commissioner of the Patent Office

- 1. International Application No. PCT/JP03/16814
- 2. Applicant

Name: Dainippon Ink and Chemicals, Inc.

Address: 35-58, Sakashita 3-chome, Itabashi-ku,

Tokyo 174-8520 JAPAN

State of nationality: JAPAN

State of residence: JAPAN

3. Representative

Name: Patent Attorney (6490), SHIGA Masatake

Address: 2-3-1, Yaesu, Chuo-ku, Tokyo 104-8453 JAPAN

- 4. Item to be Amended: Claims
- 5. Contents of Amendment:
  - (1) Claims 11 to 14 are further added.
- 6. List of Attached Documents:

Replacement sheets of claims (page 21 of Japanese specification)

## (Amendment under PCT Article 34)

- 8. The laminated sheet according to claim 5, wherein the synthetic resin films for molding contain a thermoplastic resin, and a softening point of the binder resin of the decorative layer is lower than that of the thermoplastic resin.
- 9. The laminated sheet according to claim 5, which comprises an adhesive layer at the interface between the synthetic resin film for molding and the decorative layer.
- 10. The laminated sheet according to claim 5, wherein one or more synthetic resin films for molding provided on at least one side of the decorative layer are a transparent or translucent film, and a change rate of a surface luster value of the side of the transparent or translucent synthetic resin film for molding is 20% or less at 200% malleation.
- 11. (Added) The ink according to claim 1, which substantially contains no water.
- 12. (Added) The ink according to claim 1, wherein the metal thin film fragments are obtained from a metal thin film which

is obtained by at least one method selected from the group consisting of sputtering, malleation and aluminum vapor deposition.

- 13. (Added) The laminate sheet according to claim 5, which substantially contains no water.
- 14. (Added) The laminate sheet according to claim 5, wherein the content of the metal thin film fragments is from 10 to 60% by mass based on a non-volatile component in the ink, and the binder resin contains 50 to 500 mmol/kg of at least one selected from the group consisting of a carboxyl group, a phosphoric acid group, a sulfonic acid group, metal salts thereof and an amino group.